

# High Temperature Alloys

## DATA SHEET

## C-10

METRODE PRODUCTS LTD  
 HANWORTH LANE, CHERTSEY  
 SURREY, KT16 9LL  
 Tel: +44(0)1932 566721  
 Fax: +44(0)1932 565168 Sales  
 Fax: +44(0)1932 569449 Technical  
 Fax: +44(0)1932 566199 Export  
 Email: info@metrode.com  
 Internet: http://www.metrode.com

## 308H CONSUMABLES

### Alloy type

For 304/304H materials used at elevated temperatures.

### Materials to be welded

	wrought	cast
ASTM / UNS	304H/S30409	CF10, CF8
DIN	1.4948	
BS	304S51	302C25, 304C15

### Applications

The 308H consumables are designed to match unstabilised 18Cr-10Ni austenitic stainless steels for elevated temperature strength and oxidation resistance. These steels and the weld metal have carbon content controlled to 0.04-0.08%.

Composition limits of the MMA electrodes and FCAW wires are tightened above those of BS/AWS specifications in order to meet requirements of *Shell* and other operators of refinery equipment. Weld metal Cr and Ni are kept low and ferrite is controlled to minimise embrittlement by sigma phase. Beneficial and detrimental minor elements and residuals are also controlled to optimise high temperature properties. No bismuth-bearing constituents are allowed in these consumables, to ensure <0.002%Bi as required by API 582.

The 308H consumables should also be considered for welding thick (>12mm) stabilised grades 321H or 347H to avoid in-service HAZ cracking and low creep rupture ductility associated with 347 weld metal. Note that some authorities recommend the use of type 16-8-2 types for these steels, including 304H.

308H is widely used in **petrochemical** and **chemical process plant**, particularly for the fabrication of **cyclones**, **transfer lines** used to re-circulate the catalyst in **catalytic crackers** (cat crackers) operating in the range 400-815°C.

### Microstructure

Austenite with delta ferrite controlled 2-8FN.

### Welding guidelines

Preheat not required; maximum interpass temperature 250°C. No PWHT required.

### Additional information

Farrar J.C.M. and Marshall A.W.: 'Type '300H' austenitic stainless steel weld metals for high temperature service'

Marshall A.W. and Farrar J.C.M.: 'Influence of residuals on properties of austenitic stainless steel weld metal, with particular reference to energy industries' (Conference) Stainless Steels '84, pp 271-285, Metals Society, London 1985.

There is also a Metrode Technical Profile covering the use of these products in the petrochemical industry on cat crackers.

### Related alloy groups


See also the consumables in the related alloy groups of 347H (C-11), 16.8.2 (C-12) and 316H (C-13).

### Products available

Process	Product	Specification
MMA	<b>Ultramet 308H</b>	AWS E308H-16
	<b>Ultramet B308H</b>	AWS E308H-15
TIG/MIG	<b>308S96</b>	AWS ER308H
SAW	<b>308S96</b>	AWS ER308H
	<b>SS300</b>	BS EN SA AF2
	<b>SSB</b>	BS EN SA AF2
FCW	<b>Supercore 308H</b>	AWS E308HT0-1/4
	<b>Supercore 308HP</b>	AWS E308HT1-1/4


# ULTRAMET 308H

Rutile electrode for 304H stainless steel

<b>Product description</b>	<p>MMA electrode with rutile flux on matching core wire.</p> <p>Recovery is about 110% with respect to core wire, 65% with respect to whole electrode.</p> <p><b>Ultramet 308H</b> gives both welder and weld metal all the benefits of advanced rutile electrode design. These features include optimum versatility for downhand and positional welding, combined with high cosmetic finish and full volumetric weld metal integrity.</p> <p>The smaller sizes are particularly suited to vertical and overhead welding applications including fixed pipework. In addition, the 2.5mm diameter is specifically designed to enable the root pass to be deposited in single side butt welds using standard MMA equipment without a gas purge.</p>																																																																					
<b>Specifications</b>	<table border="0"> <tr> <td><b>AWS A5.4</b></td> <td colspan="10">E308H-16</td> </tr> <tr> <td><b>BS EN 1600</b></td> <td colspan="10">E 19 9 H R 3 2</td> </tr> <tr> <td><b>BS 2926</b></td> <td colspan="10">19.9.R</td> </tr> <tr> <td><b>DIN 8556</b></td> <td colspan="10">(E 19 9 R 23)</td> </tr> </table>											<b>AWS A5.4</b>	E308H-16										<b>BS EN 1600</b>	E 19 9 H R 3 2										<b>BS 2926</b>	19.9.R										<b>DIN 8556</b>	(E 19 9 R 23)																								
<b>AWS A5.4</b>	E308H-16																																																																					
<b>BS EN 1600</b>	E 19 9 H R 3 2																																																																					
<b>BS 2926</b>	19.9.R																																																																					
<b>DIN 8556</b>	(E 19 9 R 23)																																																																					
<b>ASME IX Qualification</b>	<b>QW432</b> F-No 5, <b>QW442</b> A-No 8																																																																					
<b>Composition (weld metal wt %)</b>	<table border="1"> <thead> <tr> <th></th> <th>C</th> <th>Mn</th> <th>Si</th> <th>S</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> <th>FN</th> </tr> </thead> <tbody> <tr> <td>min</td> <td>0.04</td> <td>0.5</td> <td>--</td> <td>--</td> <td>--</td> <td>18.0</td> <td>9.0</td> <td>--</td> <td>--</td> <td>2</td> </tr> <tr> <td>max</td> <td>0.08</td> <td>1.5</td> <td>0.9</td> <td>0.025</td> <td>0.030</td> <td>21.0</td> <td>11.0</td> <td>0.25</td> <td>0.5</td> <td>8</td> </tr> <tr> <td>typ</td> <td>0.05</td> <td>1</td> <td>0.6</td> <td>0.01</td> <td>0.02</td> <td>18.5</td> <td>9.5</td> <td>0.1</td> <td>0.05</td> <td>3</td> </tr> </tbody> </table> <p>Mo + Nb + Ti = 0.25% max Note: Cr content of 2.5mm is typically 19.5%.</p>												C	Mn	Si	S	P	Cr	Ni	Mo	Cu	FN	min	0.04	0.5	--	--	--	18.0	9.0	--	--	2	max	0.08	1.5	0.9	0.025	0.030	21.0	11.0	0.25	0.5	8	typ	0.05	1	0.6	0.01	0.02	18.5	9.5	0.1	0.05	3															
	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	FN																																																												
min	0.04	0.5	--	--	--	18.0	9.0	--	--	2																																																												
max	0.08	1.5	0.9	0.025	0.030	21.0	11.0	0.25	0.5	8																																																												
typ	0.05	1	0.6	0.01	0.02	18.5	9.5	0.1	0.05	3																																																												
<b>All-weld mechanical properties</b>	<table border="1"> <thead> <tr> <th rowspan="2">As welded</th> <th rowspan="2"></th> <th rowspan="2">min</th> <th rowspan="2">typical</th> <th colspan="3">High Temperature</th> </tr> <tr> <th>650°C</th> <th>732°C</th> <th>816°C</th> </tr> </thead> <tbody> <tr> <td>Tensile strength</td> <td>MPa</td> <td>560</td> <td>610</td> <td>297</td> <td>231</td> <td>181</td> </tr> <tr> <td>0.2% Proof stress</td> <td>MPa</td> <td>350</td> <td>445</td> <td>234</td> <td>187</td> <td>156</td> </tr> <tr> <td>Elongation on 4d</td> <td>%</td> <td>35</td> <td>45</td> <td>--</td> <td>--</td> <td>--</td> </tr> <tr> <td>Elongation on 5d</td> <td>%</td> <td>30</td> <td>43</td> <td>28</td> <td>51</td> <td>53</td> </tr> <tr> <td>Reduction of area</td> <td>%</td> <td>--</td> <td>35</td> <td>55</td> <td>63</td> <td>64</td> </tr> <tr> <td>Impact energy</td> <td>+ 20°C J</td> <td>--</td> <td>80</td> <td>--</td> <td>--</td> <td>--</td> </tr> <tr> <td>Hardness</td> <td>HV</td> <td>--</td> <td>190-210</td> <td>--</td> <td>--</td> <td>--</td> </tr> </tbody> </table>											As welded		min	typical	High Temperature			650°C	732°C	816°C	Tensile strength	MPa	560	610	297	231	181	0.2% Proof stress	MPa	350	445	234	187	156	Elongation on 4d	%	35	45	--	--	--	Elongation on 5d	%	30	43	28	51	53	Reduction of area	%	--	35	55	63	64	Impact energy	+ 20°C J	--	80	--	--	--	Hardness	HV	--	190-210	--	--	--
As welded		min	typical	High Temperature																																																																		
				650°C	732°C	816°C																																																																
Tensile strength	MPa	560	610	297	231	181																																																																
0.2% Proof stress	MPa	350	445	234	187	156																																																																
Elongation on 4d	%	35	45	--	--	--																																																																
Elongation on 5d	%	30	43	28	51	53																																																																
Reduction of area	%	--	35	55	63	64																																																																
Impact energy	+ 20°C J	--	80	--	--	--																																																																
Hardness	HV	--	190-210	--	--	--																																																																
<b>Operating parameters</b>	<p>DC +ve or AC (OCV: 50V min)</p> <div style="text-align: right;">  </div> <table border="1"> <thead> <tr> <th>∅ mm</th> <th>2.5</th> <th>3.2</th> <th>4.0</th> <th>5.0</th> </tr> </thead> <tbody> <tr> <td>min A</td> <td>60</td> <td>75</td> <td>100</td> <td>130</td> </tr> <tr> <td>max A</td> <td>90</td> <td>120</td> <td>155</td> <td>210</td> </tr> </tbody> </table>											∅ mm	2.5	3.2	4.0	5.0	min A	60	75	100	130	max A	90	120	155	210																																												
∅ mm	2.5	3.2	4.0	5.0																																																																		
min A	60	75	100	130																																																																		
max A	90	120	155	210																																																																		
<b>Packaging data</b>	<table border="1"> <thead> <tr> <th>∅ mm</th> <th>2.5</th> <th>3.2</th> <th>4.0</th> <th>5.0</th> </tr> </thead> <tbody> <tr> <td>length mm</td> <td>300</td> <td>350</td> <td>350</td> <td>450</td> </tr> <tr> <td>kg/carton</td> <td>12.0</td> <td>13.5</td> <td>13.5</td> <td>17.1</td> </tr> <tr> <td>pieces/carton</td> <td>726</td> <td>414</td> <td>261</td> <td>171</td> </tr> </tbody> </table>											∅ mm	2.5	3.2	4.0	5.0	length mm	300	350	350	450	kg/carton	12.0	13.5	13.5	17.1	pieces/carton	726	414	261	171																																							
∅ mm	2.5	3.2	4.0	5.0																																																																		
length mm	300	350	350	450																																																																		
kg/carton	12.0	13.5	13.5	17.1																																																																		
pieces/carton	726	414	261	171																																																																		
<b>Storage</b>	<p><b>3 hermetically sealed ring-pull metal tins</b> per carton, with unlimited shelf life. Direct use from tin is satisfactory for much longer than a working shift of 8h. Excessive exposure of electrodes to humid conditions will cause some moisture pick-up and increase the risk of porosity.</p> <p>For electrodes that have been exposed:  <b>Redry</b> 200 – 300°C/1-2h to restore to as-packed condition. Maximum 400° C, 3 cycles, 10h total.  <b>Storage</b> of redried electrodes at 50 – 200°C in holding oven or heated quiver: no limit, but maximum 6 weeks recommended. Recommended ambient storage conditions for opened tins (using plastic lid): &lt; 60% RH, &gt; 18°C.</p>																																																																					
<b>Fume data</b>	<p>Fume composition, wt % typical:</p> <table border="1"> <thead> <tr> <th>Fe</th> <th>Mn</th> <th>Ni</th> <th>Cr</th> <th>Cu</th> <th>F</th> <th>OES (mg/m<sup>3</sup>)</th> </tr> </thead> <tbody> <tr> <td>8</td> <td>5</td> <td>0.8</td> <td>5</td> <td>&lt; 0.2</td> <td>16</td> <td>1</td> </tr> </tbody> </table>											Fe	Mn	Ni	Cr	Cu	F	OES (mg/m <sup>3</sup> )	8	5	0.8	5	< 0.2	16	1																																													
Fe	Mn	Ni	Cr	Cu	F	OES (mg/m <sup>3</sup> )																																																																
8	5	0.8	5	< 0.2	16	1																																																																

# ULTRAMET B308H

Basic pipe welding electrode for 304H stainless steel

<b>Product description</b>	<p>MMA electrode with basic carbonate-fluoride flux on matching core wire.</p> <p>Recovery is about 110% with respect to core wire, 65% with respect to whole electrode.</p> <p><b>Ultramet B308H</b> is particularly suited to positional welding, including fixed pipework qualified in the ASME 6G position, in materials thickness from 3mm up to the heaviest sections.</p>																								
<b>Specifications</b>	<b>AWS A5.4</b>		E308H-15																						
	<b>BS EN 1600</b>		E 19 9 H B 4 2																						
	<b>BS 2926</b>		19.9.B																						
	<b>DIN 8556</b>		(E 19 9 B 20+)																						
<b>ASME IX Qualification</b>	<b>QW432</b> F-No 5, <b>QW442</b> A-No 8																								
<b>Composition (weld metal wt %)</b>		C	Mn	Si	S	P	Cr	Ni	Mo	Cu	FN														
	min	0.04	0.5	--	--	--	18.0	9.0	--	--	2														
	max	0.08	2.0	0.9	0.025	0.030	21.0	11.0	0.25	0.5	8														
	typ	0.05	1	0.4	0.01	0.02	18.5	9.5	0.1	0.05	3														
	Mo + Nb + Ti = 0.25% max																								
<b>All-weld mechanical properties</b>	As welded					min	typical	High Temperature																	
								650°C	732°C	816°C															
	Tensile strength					MPa	560	650	298	225	154														
	0.2% Proof stress					MPa	350	460	223	168	111														
	Elongation on 4d					%	35	41	--	--	--														
	Elongation on 5d					%	30	38	24	48	47														
	Reduction of area					%	--	48	60	63	54														
	Impact energy					+ 20°C J	--	100	--	--	--														
Hardness					HV	--	210	--	--	--															
<b>Operating parameters</b>	DC +ve. 																								
	∅ mm	2.5		3.2		4.0		5.0																	
	min A	60		75		100		130																	
	max A	90		120		155		210																	
<b>Packaging data</b>	∅ mm	2.5		3.2		4.0		5.0																	
	length mm	300		350		350		450																	
	kg/carton	12.0		13.5		13.5		16.5																	
	pieces/carton	726		414		261		159																	
<b>Storage</b>	<p><b>3 hermetically sealed ring-pull metal tins</b> per carton, with unlimited shelf life. Direct use from tin is satisfactory for much longer than a working shift of 8h. Excessive exposure of electrodes to humid conditions will cause some moisture pick-up and increase the risk of porosity.</p> <p>For electrodes that have been exposed:</p> <p><b>Redry</b> 200 – 300°C/1-2h to restore to as-packed condition. Maximum 400° C, 3 cycles, 10h total.</p> <p><b>Storage</b> of redried electrodes at 50 – 200°C in holding oven or heated quiver: no limit, but maximum 6 weeks recommended. Recommended ambient storage conditions for opened tins (using plastic lid): &lt; 60% RH, &gt; 18°C.</p>																								
<b>Fume data</b>	<p>Fume composition, wt % typical:</p> <table border="1"> <tr> <td>Fe</td> <td>Mn</td> <td>Ni</td> <td>Cr</td> <td>Cu</td> <td>F</td> <td>OES (mg/m<sup>3</sup>)</td> </tr> <tr> <td>8</td> <td>5</td> <td>0.8</td> <td>5</td> <td>&lt; 0.2</td> <td>28</td> <td>1</td> </tr> </table>											Fe	Mn	Ni	Cr	Cu	F	OES (mg/m <sup>3</sup> )	8	5	0.8	5	< 0.2	28	1
Fe	Mn	Ni	Cr	Cu	F	OES (mg/m <sup>3</sup> )																			
8	5	0.8	5	< 0.2	28	1																			

# 308S96

Solid wire for 304H stainless steel

<b>Product description</b>	Solid wire for TIG, MIG and SAW.										
<b>Specifications</b>	<b>AWS A5.9</b>		ER308H (ER19-10H on request)								
	<b>BS EN ISO 14343-A</b>		19 9 H								
	<b>BS EN ISO 14343-B</b>		SS308H								
	<b>BS 2901: Pt2</b>		308S96								
	<b>DIN 8556</b>		(SG X5CrNi 19 9 (1.4302))								
<b>ASME IX Qualification</b>	<b>QW432</b> F-No 6, <b>QW442</b> A-No 8										
<b>Composition (wire wt %)</b>		C	Mn	Si	S	P	Cr	Ni	Mo	Cu	
	min	0.04	1.0	0.30	--	--	19.5	9.0	--	--	
	max	0.08	2.0	0.65	0.020	0.030	20.5	10.0	0.25	0.25	
	typ	0.05	1.8	0.4	0.002	0.015	19.9	9.5	0.1	0.1	
	Typical ferrite level of undiluted weld metal is in the range 3-8FN.										
	ER19-10H (on request) has Cr ≤ 20.0, Mo ≤ 0.25, Nb ≤ 0.05, Ti ≤ 0.05.										
<b>All-weld mechanical properties</b>	Typical values as welded					TIG					
	Tensile strength					MPa	630				
	0.2% Proof stress					MPa	450				
	Elongation on 4d					%	43				
	Impact energy					+ 20°C	J	> 100			
	Hardness cap/mid					HV	195/215				
<b>Typical operating parameters</b>		TIG			MIG			SAW			
	Shielding	Argon			Ar/2%O <sub>2</sub> or Ar/1-3%CO <sub>2</sub>			SS300 or SSB flux			
	Diameter	2.4mm			1.2mm			2.4mm			
	Current	100A, DC-			260A, DC+			350A, DC+			
	Voltage	12V			28V			30V			
<b>Packaging data</b>	ø mm	TIG			MIG			SAW			
	0.8	--			To order			--			
	1.0	--			To order			--			
	1.2	To order			15 kg spool			--			
	1.6	2.5kg tube			--			25kg coil			
	2.0	To order			--			--			
	2.4	2.5kg tube			--			25kg coil			
	3.2	2.5kg tube			--			To order			
<b>Fume data</b>	MIG fume composition (wt %) (TIG fume negligible):										
		Fe	Mn	Cr <sup>3</sup>	Ni	Mo	Cu	OES (mg/m <sup>3</sup> )			
		32	12	16	8	<0.5	<0.5	3.1			

# SUPERCORE 308H / 308HP

Downhand and positional FCW for 304H stainless steel

<b>Product description</b>	<p>Flux cored wires made with an austenitic stainless steel sheath and rutile flux system.</p> <p><b>Supercore 308H</b> is designed for ease of use, exceptional weld bead appearance and high weld metal integrity, primarily in downhand and H-V welding situations with plate and material of a 6mm thickness or greater. <b>Supercore 308HP</b> designed for all-positional welding from 1G/2G up to 5G/6G pipework.</p> <p>Metal recovery is about 90% with respect to wire.</p>																										
<b>Specifications</b>	<b>AWS A5.22</b> <b>BS EN ISO 17633-B</b>			<b>Supercore 308H</b> E308HT0-1/4 TS308H-FB0				<b>Supercore 308HP (1.2mm only)</b> E308HT1-1/4 TS308H-FB1																			
<b>ASME IX Qualification</b>	<b>QW432</b> F-No 6, <b>QW442</b> A-No 8																										
<b>Composition (weld metal wt %)</b>		C	Mn	Si	S	P	Cr	Ni	Mo	Cu	FN																
<b>All-weld mechanical properties</b>	As welded					min	typical	High Temperature			650°C	732°C	816°C														
	Tensile strength					MPa	550	620	287	222	163																
	0.2% Proof stress					MPa	--	420	213	177	140																
	Elongation on 4d					%	30	40	--	--	--																
	Elongation on 5d					%	30	36	30	46	40																
	Reduction of area					%	--	50	58	69	74																
	Impact energy					J	--	100	--	--	--																
	Aged at 730°C/1000h					J	--	90	--	--	--																
<b>Operating parameters</b>	<p><b>Shielding gas:</b> 80%Ar-20%CO<sub>2</sub> or 100% CO<sub>2</sub> at 20-25l/min. Proprietary gases may be used but argon should not exceed 85%.</p> <p><b>Current:</b> DC+ve ranges as below for Ar-20%CO<sub>2</sub>. Welding with 100%CO<sub>2</sub> requires approx 3V higher:</p> <table border="1" data-bbox="400 1205 1495 1328"> <thead> <tr> <th>ø mm</th> <th>amp-volt range</th> <th>typical</th> <th>stickout</th> </tr> </thead> <tbody> <tr> <td>1.2</td> <td>120A-22V to 280A-34V</td> <td>180A-29V</td> <td>12 – 20mm</td> </tr> <tr> <td>1.2 (positional)</td> <td>120A-22V to 250A-32V</td> <td>150A-25V</td> <td>12 – 20mm</td> </tr> <tr> <td>1.6</td> <td>200A-28V to 330A-34V</td> <td>230A-30V</td> <td>15 – 25mm</td> </tr> </tbody> </table>											ø mm	amp-volt range	typical	stickout	1.2	120A-22V to 280A-34V	180A-29V	12 – 20mm	1.2 (positional)	120A-22V to 250A-32V	150A-25V	12 – 20mm	1.6	200A-28V to 330A-34V	230A-30V	15 – 25mm
ø mm	amp-volt range	typical	stickout																								
1.2	120A-22V to 280A-34V	180A-29V	12 – 20mm																								
1.2 (positional)	120A-22V to 250A-32V	150A-25V	12 – 20mm																								
1.6	200A-28V to 330A-34V	230A-30V	15 – 25mm																								
<b>Packaging data</b>	<p>Spools vacuum-sealed in barrier foil with cardboard carton: 15kg</p> <p>The as-packed shelf life is virtually indefinite.</p> <p>Resistance to moisture absorption is high, but to prevent any possibility of porosity it is advised that part-used spools are returned to polythene wrappers.</p> <p>Where possible, preferred storage conditions are 60% RH maximum, 18°C minimum.</p>																										
<b>Fume data</b>	<p>Fume composition (wt %):</p> <table border="1" data-bbox="400 1552 1495 1619"> <thead> <tr> <th>Fe</th> <th>Mn</th> <th>Ni</th> <th>Cr<sup>3</sup></th> <th>Cr<sup>6</sup></th> <th>Cu</th> <th>F</th> <th>OES (mg/m<sup>3</sup>)</th> </tr> </thead> <tbody> <tr> <td>17</td> <td>11</td> <td>2</td> <td>4</td> <td>5</td> <td>&lt;1</td> <td>5</td> <td>1</td> </tr> </tbody> </table>											Fe	Mn	Ni	Cr <sup>3</sup>	Cr <sup>6</sup>	Cu	F	OES (mg/m <sup>3</sup> )	17	11	2	4	5	<1	5	1
Fe	Mn	Ni	Cr <sup>3</sup>	Cr <sup>6</sup>	Cu	F	OES (mg/m <sup>3</sup> )																				
17	11	2	4	5	<1	5	1																				